

In re: Williams *et al.*  
Serial No.: 10/662,621  
Filed: September 15, 2003  
Page 2 of 18

**In the Claims:**

1. (Currently Amended) A method of producing a biocompatible intraluminal prosthesis for *in vivo* use, comprising:  
providing an intraluminal prosthesis having a portion thereof formed from polymeric material, wherein the polymeric material contains one or more toxic materials;  
masking one or more portions of the polymeric material;  
immersing the polymeric material in a densified carbon dioxide composition such that the toxic materials are absorbed from unmasked portions of the polymeric material by the densified carbon dioxide composition; and  
removing the densified carbon dioxide composition containing the toxic materials from the polymeric material, such that the intraluminal prosthesis is suitable for *in vivo* use.
2. (Original) The method of Claim 1, wherein the one or more toxic materials are selected from the group consisting of organic solvents (polar or non-polar), unpolymerized monomers, polymerization catalysts, oligomers, and polymerization initiators.
3. (Original) The method of Claim 1, wherein the densified carbon dioxide composition is a liquid composition, and wherein the immersing and removing steps are carried out in an enclosed chamber.
4. (Original) The method of Claim 1, wherein the immersing step comprises adjusting the pressure and/or temperature of the densified carbon dioxide composition to selectively absorb toxic materials from the polymeric material.
5. (Original) The method of Claim 1, further comprising:  
lowering the density of the removed densified carbon dioxide composition such that the toxic materials entrained therein become separated therefrom; and  
removing the separated toxic materials.

In re: Williams *et al.*  
Serial No.: 10/662,621  
Filed: September 15, 2003  
Page 3 of 18

6. (Original) The method of Claim 5, wherein the step of lowering the density comprises reducing pressure and/or increasing temperature of the densified carbon dioxide composition.

7. (Original) The method of Claim 1, wherein carbon dioxide in the densified carbon dioxide composition is present in a supercritical state.

8. (Original) The method of Claim 1, wherein the carbon dioxide contains one or more of a co-solvent, a surfactant, and a co-surfactant.

9. (Original) The method of Claim 1, wherein the intraluminal prosthesis is a stent.

10. (Cancelled)

11. (Original) The method of Claim 1, wherein the polymeric material is erodible.

12. (Original) The method of Claim 1, wherein the polymeric material is non-erodible.

13. (Original) The method of Claim 1, wherein the polymeric material is a coating on one or more portions of the intraluminal prosthesis.

14. (Original) The method of Claim 11, wherein the erodible polymeric material is selected from the group consisting of, surgical gut, silk, cotton, liposomes, poly(hydroxybutyrate), polycarbonate, polyacrylate, polyanhydride, polyethylene glycol, poly(ortho esters), poly(phosphoesters), polyesters, polyamides, polyphosphazenes, poly(*p*-dioxane), poly(amino acid), polyglactin, erodible hydrogels, collagen, chitosan, poly(lactic acid), poly(L-lactic acid), poly(D,L-lactic acid), poly(glycolic acid), poly(D-lactic-co-

In re: Williams *et al.*  
Serial No.: 10/662,621  
Filed: September 15, 2003  
Page 4 of 18

glycolic acid), poly(L-lactic-co-glycolic acid), poly(D,L-lactic-co-glycolic acid), poly(ε-caprolactone), poly(valerolactone), poly(hydroxy butyrate), poly(hydrovalerate), polydioxanone, poly(propylene fumarate), poly(ethyleneoxide)-poly(butylene tetraphthalate), poly(lactic acid-co-lysine), poly(L-lactic acid) and poly(ε-caprolactone) copolymers.

15. (Currently Amended) A method of producing a biocompatible intraluminal prosthesis for *in vivo* use, comprising:

providing an intraluminal prosthesis having a portion thereof formed from erodible polymeric material selected from the group consisting of: surgical gut, silk, cotton, liposomes, poly(hydroxybutyrate), polycarbonate, polyacrylate, polyanhydride, polyethylene glycol, poly(ortho esters), poly(phosphoesters), polyesters, polyamides, polyphosphazenes, poly(p-dioxane), poly(amino acid), polyglactin, erodible hydrogels, collagen, chitosan, poly(lactic acid), poly(L-lactic acid), poly(D,L-lactic acid), poly(glycolic acid), poly(D-lactic-co-glycolic acid), poly(L-lactic-co-glycolic acid), poly(D,L-lactic-co-glycolic acid), poly(ε-caprolactone), poly(valerolactone), poly(hydroxy butyrate), poly(hydrovalerate), polydioxanone, poly(propylene fumarate), poly(ethyleneoxide)-poly(butylene tetraphthalate), poly(lactic acid-co-lysine), poly(L-lactic acid) and poly(ε-caprolactone) copolymers, wherein the polymeric material contains one or more toxic materials;

immersing the polymeric material in a densified carbon dioxide composition such that the toxic materials are absorbed by the densified carbon dioxide composition, wherein pressure and/or temperature of the densified carbon dioxide composition is adjusted to selectively absorb toxic materials from the polymeric material;

removing the densified carbon dioxide composition containing the toxic materials from the polymeric material;

lowering the density of the removed densified carbon dioxide composition such that the toxic materials entrained therein become separated therefrom; and

removing the separated toxic materials, such that the intraluminal prosthesis is suitable for *in vivo* use.

In re: Williams *et al.*  
Serial No.: 10/662,621  
Filed: September 15, 2003  
Page 5 of 18

16. (Original) The method of Claim 15, wherein the one or more toxic materials are selected from the group consisting of organic solvents (polar or non-polar), unpolymerized monomers, polymerization catalysts, oligomers, and polymerization initiators.

17. (Original) The method of Claim 15, wherein the densified carbon dioxide composition is a liquid composition, and wherein the immersing and removing steps are carried out in an enclosed chamber.

18. (Original) The method of Claim 15, wherein the step of lowering the density comprises reducing pressure and/or increasing temperature of the densified carbon dioxide composition.

19. (Original) The method of Claim 15, wherein carbon dioxide in the densified carbon dioxide composition is present in a supercritical state.

20. (Original) The method of Claim 15, wherein the intraluminal prosthesis is a stent.

21. (Previously Presented) The method of Claim 15, further comprising masking one or more portions of the polymeric material prior to immersing the polymeric material in a densified carbon dioxide composition, such that toxic materials are absorbed from unmasked portions of the polymeric material.

22. (Cancelled)

23. (Currently Amended) The method of Claim 15, wherein the intraluminal prosthesis comprises a portion thereof that is formed from non-erodible polymeric material ~~is non-erodible~~.

In re: Williams *et al.*  
Serial No.: 10/662,621  
Filed: September 15, 2003  
Page 6 of 18

24. (Original) The method of Claim 15, wherein the carbon dioxide contains one or more of a co-solvent, a surfactant, and a co-surfactant.

25. (Original) The method of Claim 15, wherein the polymeric material is a coating on one or more portions of the intraluminal prosthesis.

26. (Cancelled)